

NATIONAL AERONAUTICS AND SPACE ADMINISTRATION

Technical Memorandum 33-564

*A Basic Model for Acoustic Emission
From Fiber-Reinforced Material*

E. Y. Robinson

(NASA-CR-128344) A BASIC MODEL FOR
ACOUSTIC EMISSION FROM FIBER-REINFORCED
MATERIAL E.Y. Robinson (Jet Propulsion
Lab.) 1 Sep. 1972 6 p
N72-33562
CSCL 11D
G3/18
Unclas
44061

JET PROPULSION LABORATORY
CALIFORNIA INSTITUTE OF TECHNOLOGY
PASADENA, CALIFORNIA

September 1, 1972

Reproduced by
NATIONAL TECHNICAL
INFORMATION SERVICE
U S Department of Commerce
Springfield VA 22151



1. Report No. 33-564	2. Government Accession No.	3. Recipient's Catalog No.	
4. Title and Subtitle A BASIC MODEL FOR ACOUSTIC EMISSION FROM FIBER-REINFORCED MATERIAL		5. Report Date September 1, 1972	
		6. Performing Organization Code	
7. Author(s) E. Y. Robinson		8. Performing Organization Report No.	
9. Performing Organization Name and Address JET PROPULSION LABORATORY California Institute of Technology 4800 Oak Grove Drive Pasadena, California 91103		10. Work Unit No.	
		11. Contract or Grant No. NAS 7-100	
12. Sponsoring Agency Name and Address NATIONAL AERONAUTICS AND SPACE ADMINISTRATION Washington, D.C. 20546		13. Type of Report and Period Covered Technical Memorandum	
		14. Sponsoring Agency Code	
15. Supplementary Notes			
16. Abstract Acoustic Emission (AE) from fiber-reinforced composites can often be conveniently interpreted by use of normalized coordinates in graphical data display. Many aspects of the shape of the acoustic emission pattern are invariant with the signal amplification ratio, and the use of normalized coordinates allows simultaneous comparison of AE pattern shapes from different experiments. In this paper, the first-order model of AE from fiber composites, based on filament breaking rates, is cast into a normalized form useful for correlating experimental data. The general features of the normalized model are shown and compare favorably with available data.			
17. Key Words (Selected by Author(s)) Acoustics Materials, Nonmetallic Solid-State Physics Structural Engineering		18. Distribution Statement Unclassified -- Unlimited	
19. Security Classif. (of this report) Unclassified	20. Security Classif. (of this page) Unclassified	21. No. of Pages 5	22. Price

HOW TO FILL OUT THE TECHNICAL REPORT STANDARD TITLE PAGE

Make items 1, 4, 5, 9, 12, and 13 agree with the corresponding information on the report cover. Use all capital letters for title (item 4). Leave items 2, 6, and 14 blank. Complete the remaining items as follows:

3. Recipient's Catalog No. Reserved for use by report recipients.
7. Author(s). Include corresponding information from the report cover. In addition, list the affiliation of an author if it differs from that of the performing organization.
8. Performing Organization Report No. Insert if performing organization wishes to assign this number.
10. Work Unit No. Use the agency-wide code (for example, 923-50-10-06-72), which uniquely identifies the work unit under which the work was authorized. Non-NASA performing organizations will leave this blank.
11. Insert the number of the contract or grant under which the report was prepared.
15. Supplementary Notes. Enter information not included elsewhere but useful, such as: Prepared in cooperation with... Translation of (or by)... Presented at conference of... To be published in...
16. Abstract. Include a brief (not to exceed 200 words) factual summary of the most significant information contained in the report. If possible, the abstract of a classified report should be unclassified. If the report contains a significant bibliography or literature survey, mention it here.
17. Key Words. Insert terms or short phrases selected by the author that identify the principal subjects covered in the report, and that are sufficiently specific and precise to be used for cataloging.
18. Distribution Statement. Enter one of the authorized statements used to denote releasability to the public or a limitation on dissemination for reasons other than security of defense information. Authorized statements are "Unclassified-Unlimited," "U.S. Government and Contractors only," "U.S. Government Agencies only," and "NASA and NASA Contractors only."
19. Security Classification (of report). NOTE: Reports carrying a security classification will require additional markings giving security and downgrading information as specified by the Security Requirements Checklist and the DoD Industrial Security Manual (DoD 5220.22-M).
20. Security Classification (of this page). NOTE: Because this page may be used in preparing announcements, bibliographies, and data banks, it should be unclassified if possible. If a classification is required, indicate separately the classification of the title and the abstract by following these items with either "(U)" for unclassified, or "(C)" or "(S)" as applicable for classified items.
21. No. of Pages. Insert the number of pages.
22. Price. Insert the price set by the Clearinghouse for Federal Scientific and Technical Information or the Government Printing Office, if known.

NATIONAL AERONAUTICS AND SPACE ADMINISTRATION

Technical Memorandum 33-564


*A Basic Model for Acoustic Emission
From Fiber-Reinforced Material*

E. Y. Robinson

JET PROPULSION LABORATORY
CALIFORNIA INSTITUTE OF TECHNOLOGY
PASADENA, CALIFORNIA

September 1, 1972

Prepared Under Contract No. NAS 7-100
National Aeronautics and Space Administration



JET PROPULSION LABORATORY California Institute of Technology • 4800 Oak Grove Drive, Pasadena, California 91103

September 21, 1972

Recipients of Jet Propulsion Laboratory
Technical Memorandum 33-564:

Please note the following corrections to Technical Memorandum 33-564,
A Basic Model for Acoustic Emission From Fiber-Reinforced Material, by
E. Y. Robinson, dated September 1, 1972:

Equation (3) on page 2 should read

$$\sigma^* = \frac{S(\sigma^*)}{f(\sigma^*)} \quad \text{instead of} \quad \sigma^* = \frac{f(\sigma^*)}{S(\sigma^*)}$$

Therefore, the equation at the bottom of page 2 should read

$$\sigma^* = -\frac{1}{K(\sigma^*)} \quad \text{instead of} \quad \sigma^* = -K(\sigma^*)$$

Very truly yours,

John Kempton, Manager
Publications Section

I (L)

PRECEDING PAGE BLANK NOT FILMED

PREFACE

The work described in this report was performed by the Engineering Mechanics Division of the Jet Propulsion Laboratory.

Preceding page blank

PRECEDING PAGE BLANK NOT FILMED

CONTENTS

I.	Introduction	1
II.	Acoustic Emission Model	2
	References	4

FIGURE

1.	Normalized acoustic emission vs load; analytical predictions and data from graphite-carbon and boron/epoxy composites	5
----	---	---

Preceding page blank

ABSTRACT

Acoustic Emission (AE) from fiber-reinforced composites can often be conveniently interpreted by use of normalized coordinates in graphical data display. Many aspects of the shape of the acoustic emission pattern are invariant with the signal amplification ratio, and the use of normalized coordinates allows simultaneous comparison of AE pattern shapes from different experiments. In this paper, the first-order model of AE from fiber composites, based on filament breaking rates, is cast into a normalized form useful for correlating experimental data. The general features of the normalized model are shown and compare favorably with available data.

I. INTRODUCTION

Interest and investigation are increasing in the area of acoustic emission (AE), and studies are proceeding (Ref. 1) with application to a variety of materials and structures, including fiber-reinforced systems. The techniques used vary in detail but are commonly concerned with the detection of faint, high-frequency stress waves emanating from sources of sudden energy release such as dislocation advances, phase changes, crack propagation, internal friction and sliding, etc. Much work remains to be done on signal processing and data interpretation, but certain basic trends have emerged from the work done on fiber-reinforced systems at various laboratories (Ref. 1). The classic AE pattern for linear loading is a nominally monotonic increase in AE at an increasing rate. It appears possible to distinguish, in some cases, between two types of emission: (1) the emission due to fiber fracture from emission sources in the matrix and (2) emission at the interface of fiber and matrix (Ref. 2). The emission from fiber breaks appears to be more intense and distinct than matrix-related AE. While basic acoustic emission phenomena are apparently quite complex and must depend on microscopic structural details and local stress states, it is desirable to have at least a first-order model of AE from fiber composites to aid interpretation of data trends and to provide a baseline from which refinements of analytical models can proceed.

II. ACOUSTIC EMISSION MODEL

The purpose of this note is to define a basic first-order mechanism for acoustic emission from fiber composites undergoing monotonic loading to failure. The essential premises are that AE phenomena are dominated by the events of filament failure throughout the loading, and that the filament stress σ is carried uniformly by the reinforcing filaments. Unidirectional reinforcement is assumed, with filament strength distribution given by the cumulative survivability function $S(\sigma)$. The filament failure rate is then proportional to the AE rate. The integrated acoustic emission, ΣAE , is expressed proportionally as

$$\Sigma AE \propto 1 - S(\sigma) \quad (1)$$

It is generally convenient to normalize ΣAE so that shape trends of data which differ in absolute scale may be compared. This also avoids the absolute specification of a proportionality constant. The maximum ΣAE at the onset of final failure is taken as the normalizing level. The strength of an idealized bundle of reinforcing filaments is reached when the nominal stress

$$\sigma_{\text{nom}} = \sigma S(\sigma) \quad (2)$$

is maximum. This maximum occurs at a critical value of σ , denoted by σ^* , which in the usual cases satisfies:

$$\sigma^* = \frac{f(\sigma^*)}{S(\sigma^*)} \quad (3)$$

where $f(\sigma)$ is the frequency distribution. Exponential statistical distributions are often characterized by the property

$$f(\sigma) = -K(\sigma)S(\sigma)$$

and the critical stress σ^* is then a solution of

$$\sigma^* = -K(\sigma^*)$$

and $S(\sigma^*)$ may be evaluated by direct substitution of σ^* .

The normalized acoustic emission E is given by

$$E = \frac{1 - S(\sigma)}{1 - S(\sigma^*)} \quad (4)$$

The external loading, expressed as a nominal stress, is given by Eq. (2). It is desirable in many cases to normalize the applied load also, using the maximum load at failure as the normalizing factor. This normalized load P is

$$P = \frac{\sigma_{\text{nom}}}{\sigma_{\text{nom}_{\text{max}}}} = \frac{\sigma S(\sigma)}{\sigma^* S(\sigma^*)} \quad (5)$$

The relation between E and P can be written in closed form if $S(\sigma)$ can be inverted to give an expression for σ .

$$\sigma = \mathcal{H}\{S\} \quad (6)$$

Eliminating S between Eqs. (4) and (5) yields

$$P = \frac{\mathcal{H}\{1 - E(1 - S(\sigma^*))\} [1 - E(1 - S(\sigma^*))]}{\sigma^* S(\sigma^*)} \quad (7)$$

Note that the braces identify the argument of the inversion \mathcal{H} .

Equation 7 is the mathematical expression of the proposed basic AE model for unidirectional fiber-reinforced systems. Other basic assumptions can lead to similar functional relationships, and Eq. (7) is likely to be a useful algebraic form even in cases which do not meet the stated premises.

This model of acoustic emission will be illustrated using a Weibull distribution for S:

$$S = \exp(-C\sigma^m)$$

$$K(\sigma) = -(mC\sigma^{m-1})$$

$$\sigma^* = (1/Cm)^{1/m}$$

$$S(\sigma^*) = \exp(-1/m)$$

$$\sigma = \mathcal{H}(S) = [(1/C) \ln 1/S]^{1/m}$$

Putting these terms into Eq. (7) gives

$$P = \left\{ 1 - E[1 - \exp(-1/m)] \right\} \left[m \ln \frac{1}{1 - E[1 - \exp(-1/m)]} \right]^{1/m} \quad (8)$$

The contours relating P and E by this equation are shown in Fig. 1. The curvature trend shown, a slight downward convexity, is consistent with some preliminary data on boron/epoxy and graphite/carbon specimens. These data are superimposed on Fig. 1. A rough rule of thumb which may be extracted from Eq. (7) is

$$E \approx P^m$$

This rule of thumb displays a relationship between the statistical dispersion m of the acoustic source and the experimentally measured variables P and E.

REFERENCES

1. Liptai, R. G., Harris, D. O., Engle, R. B., and Tatro, C. H., "Acoustic Emission Techniques in Materials Research," International Journal of Nondestructive Testing, Vol. 3, pp. 215-275, 1971.
2. Mullin, J. V., Mazzio, V. F., and Mehan, R. L., Basic Failure Mechanisms in Advanced Composites, NASA Progress Report, Contract NASw - 2093. Space Sciences Laboratory, General Electric Company, Oct. 1971.




Fig. 1. Normalized acoustic emission vs load; analytical predictions and data from graphite-carbon and boron/epoxy composites